This listing of claims will replace all prior versions, and listings of claims in the application:

Listing of Claims:

1.   (Previously Presented) A method of preferentially forming single walled carbon nanotubes having a particular diameter, comprising:

providing a catalyst comprising:

Co and Mo disposed on a support material wherein the majority of the Mo occurs as dispersed Mo oxide clusters and the majority of the Co occurs as $CoMoO_4$ with the Co therein primarily in an octahedral configuration, and wherein the $CoMoO_4$ occurs substantially disposed upon the dispersed Mo oxide clusters; and

exposing the catalyst in a reactor to a carbon-containing gas at a temperature between about 700°C and about 800°C and maintaining a CO_2 concentration in the reactor below a threshold CO_2 concentration above which the conversion of ionic Co to metallic Co is inhibited, wherein the majority of the single walled carbon nanotubes thus formed have a diameter between about .7 nm to about .9 nm.

2.   (Previously Presented) The method of claim 1 wherein in the step of providing a catalyst, the support material is silica.

3.   (Previously Presented) The method of claim 1 wherein in the step of exposing the catalyst to a carbon-containing gas, the reactor has a pressure therein between about 1 atm and 7 atm.

4.   (Previously Presented) The method of claim 1 wherein in the step of exposing the catalyst to a carbon-containing gas, the threshold CO_2 concentration in the reactor is 1%.

5.   (Previously Presented) The method of claim 1 wherein in the step of exposing the catalyst to a carbon-containing gas, the carbon-containing gas is CO.

6.   (Previously Presented) The method of claim 1 comprising the additional step of reducing the catalyst by exposing the catalyst to a heated hydrogen gas.

7.   (Cancelled)

8.   (Previously Presented) A method of preferentially forming single walled carbon nanotubes having a particular diameter, comprising:

providing a catalyst comprising:

Co and Mo disposed on a support material wherein the majority of the Mo

occurs as dispersed Mo oxide clusters and the majority of the Co occurs as $CoMoO_4$ with the Co therein primarily in an octahedral configuration, and wherein the $CoMoO_4$ occurs substantially disposed upon the dispersed Mo oxide clusters; and

exposing the catalyst in a reactor to a carbon-containing gas at a temperature between about 800°C and about 900°C and maintaining a CO_2 concentration in the reactor below a threshold CO_2 concentration above which the conversion of ionic Co to metallic Co is inhibited, wherein the majority of the single walled carbon nanotubes thus formed have a diameter between about .9 nm to about 1.2 nm.

9.   (Previously Presented) The method of claim 8 wherein in the step of providing a catalyst, the support material is silica.

10.   (Previously Presented) The method of claim 8 wherein in the step of exposing the catalyst to a carbon-containing gas, the reactor has a pressure therein between about 1 atm and 7 atm.

11.   (Previously Presented) The method of claim 8 wherein in the step of exposing the catalyst to a carbon-containing gas, the threshold CO_2

4

concentration in the reactor is 1%.

12.   (Previously Presented) The method of claim 8 wherein in the step of exposing the catalyst to a carbon-containing gas, the carbon containing gas is CO.

13.   (Previously Presented) The method of claim 8 comprising the additional step of reducing the catalyst by exposing the catalyst to a heated hydrogen gas.

14.   (Cancelled)

15.   (Previously Presented) A method of preferentially forming single walled carbon nanotubes having a particular diameter, comprising:

providing a catalyst comprising:

Co and Mo disposed on a support material wherein the majority of the Mo occurs as dispersed Mo oxide clusters and the majority of the Co occurs as $CoMoO_4$ with the Co therein primarily in an octahedral configuration, and wherein the $CoMoO_4$ occurs substantially disposed upon the dispersed Mo oxide clusters; and

exposing the catalyst in a reactor to a carbon-containing gas at a temperature between about 900°C and about 1,000°C and

maintaining a CO_2 concentration in the reactor below a threshold CO_2 concentration above which the conversion of ionic Co to metallic Co is inhibited, wherein the majority of the single walled carbon nanotubes thus formed have a diameter between about 1.3 nm to about 1.7 nm.

16.   (Previously Presented) The method of claim 15 wherein in the step of providing a catalyst, the support material is silica.

17.   (Previously Presented) The method of claim 15 wherein in the step of exposing the catalyst to a carbon-containing gas, the reactor has a pressure therein between about 1 atm and 7 atm.

18.   (Previously Presented) The method of claim 15 wherein in the step of exposing the catalyst to a carbon-containing gas, the threshold CO_2 concentration in the reactor is 1%.

19.   (Previously Presented) The method of claim 15 wherein in the step of exposing the catalyst to a carbon-containing gas, the carbon-containing gas is CO.

20.   (Previously Presented) The method of claim 15 comprising the additional step of reducing the catalyst by exposing the catalyst to a heated hydrogen gas.

21.   (Cancelled)

22.   (Previously Presented) The method of claim 1 wherein in the step of providing the catalyst, the Mo oxide clusters comprise Mo oxide clusters having a domain size between that of MoO_3 and heptamolybdate.

23.   (Previously Presented) The method of claim 1 wherein in the step of providing the catalyst, the catalyst has a molar ratio of Co:Mo of less than 3:4.

24.   (Previously Presented) The method of claim 8 wherein in the step of providing the catalyst, the Mo oxide clusters comprise Mo oxide clusters having a domain size between that of MoO_3 and heptamolybdate.

25.   (Previously Presented) The method of claim 8 wherein in the step of providing the catalyst, the catalyst has a molar ratio of Co:Mo of less than 3:4.

26.   (Previously Presented) The method of claim 15 wherein in the step of providing the catalyst, the Mo oxide clusters comprise Mo oxide clusters having

a domain size between that of MoO_3 and heptamolybdate.

27.   (Previously Presented) The method of claim 15 wherein in the step of providing the catalyst, the catalyst has a molar ratio of Co:Mo of less than 3:4.